

HEMP FJORD & SPICED

Fjord

Composition: 67% PL HUV, 33% HEMP/CA

Weight: 300 gr / m² +/- 5%

Roll Width: 140 cm +/- 3%

Roll Length: 20 - 25 meters

Repeat: -

Abrasion resistance: >20.000 cycles Martindale +/- 10% UNI EN ISO 12947-2:2000

Pilling: Grade 4 (change at 5000 turns) UNI EN ISO 12945-2:2002

Dry clean fastness: Colour change 4-5 UNI EN ISO D01:1995

Rub fastness: Dry 4-5 / Wet 3 UNI EN ISO 105-X12:1995

**Light fastness weathering: Light colour 6 / Medium-Dark colour 6/7 UNI EN ISO 105-B04/00
Weathering**

Fastness to Chlorinated water: 4-5 UNI EN ISO 105 E03:2010

Treated: ECO Silicon-Water Repellent-Soil & Stain resistant

**Flame resistance: BS 5852:2006 Cigarette under test / BS 5852:2006 Match under test / CAL
TB 117-2013 Under test**

Spiced

Composition: 70% PL HUV, 30% HEMP/CA

Weight: 486 gr / m² +/- 5%

Roll Width: 140 cm +/- 3%

Roll Length: 20 - 25 meters

Repeat: warp 1,5 cm - weft 1,1 cm

Abrasion resistance: >10.000 cycles Martindale +/- 10% UNI EN ISO 12947-2:2000

Pilling: Grade 4 (change at 5000 turns) UNI EN ISO 12945-2:2002

Dry clean fastness: Colour change 4-5 UNI EN ISO D01:1995

Rub fastness: Dry 4-5 / Wet 3 UNI EN ISO 105-X12:1995

**Light fastness weathering: Light colour 6 / Medium-Dark colour 6/7 UNI EN ISO 105-B04/00
Weathering**

Fastness to Chlorinated water: 4-5 UNI EN ISO 105 E03:2010

Treated: ECO Silicon-Water Repellent-Soil & Stain resistant

**Flame resistance: BS 5852:2006 Cigarette under test / BS 5852:2006 Match under test / CAL
TB 117-2013 Under test**