

# FIRE TECHNOLOGY SERVICES

# **Confidential Report**

Our Ref: 27/03523A/05/15







> Tel: +44 (0)113 259 1999 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

> > Page 1 of 4

19 May 2015

Our Ref: 27/03523A/05/15

Your Ref:

Client: Vyva Fabrics

Frankfurtstraat 29/31

1171 RH Lijnden

The Netherlands

Job Title: Fire Test on One Sample of Fabric

Clients Order Ref:

Date of Receipt: 5 May 2015

One sample of fabric, referenced: **Colourways**. Description of Sample:

Work Requested: Fire Technology Services were requested to carry out a fire test on

the sample supplied to BS 5852 Source 5.







Tel: +44 (0)113 259 1999 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

19 May 2015 Page 2 of 4

Our Ref: 27/03523A/05/15

Your Ref:

### **Vyva Fabrics**

FIRE TESTS ACCORDING TO BS 5852:2006 (2011)

Methods of test for assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources

Date of Test: 19/05/15

## Conditioning

Immediately prior to testing the sample was placed in indoor ambient conditions for 72 hours and then conditioned in a standard atmosphere of 20 5°C temperature and 50 20% relative humidity for at least 16 hours.

The sample was tested in a room of volume 25m<sup>3</sup> and 22°C

#### **Procedure**

The test was carried out in accordance with BS 5852:2006. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

The specimen of fabric was mounted over fillings of combustion modified high resilience foam of density about 35 kg/m<sup>3</sup>.

The test was made using ignition source 5 in accordance with Section 11 'Methods of test for the ignitability of upholstery composites' and pass classifications were assigned for each ignition source if the performance requirements stated below were met.

## Requirements

Ignition Source	Maximum duration allowed for progressive smouldering	Maximum duration allowed for flaming
2	15 min after removal of burner tube	120 seconds after removal of burner tube
3	13 milit after removal of burner tube	
4	60 minutes after ignition of wood	10 minutes after ignition of wood crib
5	crib	
6	60 minutes after ignition of wood	13 minutes after ignition of
7	crib	wood crib





> Tel: +44 (0)113 259 1999 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

19 May 2015 Page 3 of 4

Our Ref: 27/03523A/05/15

Your Ref:

### **Vyva Fabrics**

## Requirements (Continued)

#### Failure also occurs if:

- smouldering or flaming necessitates forcible extinction due to escalating combustion behaviour so it is unsafe to continue
- flaming or smouldering essentially consumes the specimen within the test duration
- smouldering reaches the extremities of the specimen, that is to either side or to the full thickness of
- flaming reaches the extremities of the specimen other than the top of the vertical part of the test specimen
- flaming passes through the full thickness of the specimen within the test duration
- any specimen that on final examination shows evidence of charring, within the filling 100 mm from the nearest part of the original position of the source
- any debris that causes an isolated floor fire that does not meet the requirements stated in the above table

# Results

The test results relate only to the ignitability of the combination of upholstery composites under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the materials or products in use.

	Source 5	
	(Top)	
Time of ignition(s)	30	52
Time of Flame Extinction(s)	300	312
Time of Smoke Extinction(s)	487	438
Time of cover split(s)	153	120
Damage on seat width (mm)	90	80
Damage on seat length (mm)	55	50
Damage on seat depth (mm)	22	30
Damage on back width (mm)	70	80
Damage on back length (mm)	300	305
Damage on back depth (mm)	25	20
Melting (Yes or No)	Yes	Yes
Dripping (Yes or No)	No	No
Charring (Yes or No)	Yes	Yes
Other Phenomena		
Pass/Fail	Pass	Pass







Tel: +44 (0)113 259 1999 Web:http://www.bttg.co.uk Email:CSLeeds@bttg.co.uk

19 May 2015 Page 4 of 4

Our Ref: 27/03523A/05/15

Your Ref:

# **Vyva Fabrics**

#### Note

The specimens were tested after a water soaking procedure specified in BS 5651:1978, except for:

After 30 minutes, the specimen was removed, rinsed in water using a liquor ratio of 1:20 for 2 minutes, and then dried by hanging the fabric until it has dripped dry and then placing back into conditioning as stated above.

#### Comment

The results indicate that the above sample met the performance requirements for source 5

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.

Reported by: B Marsden (Mrs), Fire Technician

Enquiries concerning this report should be addressed to Customer Services.



