

CATAS S.p.A. Iscr. Reg. Imprese Udine nr. iscr. C.F. 01818850305 Reg. Impr. UD 20663 P. IVA: 01818850305 C.Soc. € 1.003.650,00 i.v.

Sede: Via Antica, 24/3 33048 S. Giovanni al Nat. UD Tel. 0432.747211 r.a. Fax 0432.747250 http://www.catas.com e-mail: lab@catas.com Filiale: Via Braille, 5 20851 Lissone MB Tel. 039.464567 Fax 039.464565 e-mail: lissone@catas.com

TEST REPORT

192848 / 1

Date received:

18/03/15

Date of test:

01/04/15

Date of issue:

01/04/15

Sample name:

Upholstered furniture covered with art. "Harlow"

Supplied by Vyva Fabrics TT. Vasumweg 140 1033 SH Amsterdam The Netherlands

Small flame applied on upholstered furniture UNI 9175:2010

Description of materials as declared by the client

Cover material: composition PVC - polyester, mass per unit area 650 g/m², thickness 1,0 mm.

The exposed surface of the cover was tested.

Filling material (supplied by Laboratory as requested by the client): class 1.IM polyurethane foam, density 25 kg/m³.

End use: upholstered furniture.

Deviations from the standard as requested by the client

None.

Preliminaries

Sampling procedure and cutting direction of the cover material specimens: performed by the client.

Preparation of cover material: UNI 9176:2010 method D.

Conditioning

Cover material: drying procedure for a minimum of 24 hours in a oven with forced air circulation at 40 ± 5 °C following a minimum of 48 hours at 23 ± 2 °C and 50 ± 5 % relative humidity.

Filling material: 72 hours at 80 \pm 5 °C and 80 \pm 5 % relative humidity following a minimum of 48 hours at 23 \pm 2 °C and 50 \pm 5 % relative humidity.

Test results

Materials tested	Tests	Test results according to ignition source times								
		20 s	tpc (s)	tpi (s)	80 s	tpc (s)	tpi (s)	140 s	tpc (s)	tpi (s)
Filling material	1st	Pass	0	0						
	2nd	Pass	0	0						
Cover material	1st	Pass	0	0	Pass	6	0	Pass	4	0
Filling material	2nd	Pass	0	0	Pass	5	0	Pass	3	0
	3th	=			=			=		

Notes: /

tpc: post-combustion time.

tpi: post-incandescence time.

The cover material of the composite of the 1st sample has been obtained with the long side parallel to the longitudinal direction. The cover material of the composite of the 2nd sample has been obtained with the long side parallel to the transversal direction. Based on test results, the sample examined complies with class 1.IM (ONE I M).

This test report is not issued according to articles 8 and 10 of D.M. 26-06-1984 amended by D.M. 03-09-2001.

Head of Department

S.GIOVANNI AL NATISONE (UD)

Managing Director Dr. Andrea Giavon

The sample name and, when relevant, its description, are given by the preerer, and CATAS does not assume responsibility of this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer.