

^{*} is also available in BS5852 Part 2 CRIB 5 ** is also availal









CHARACTERISTICS		INDOOR
Composition:	Topcoat: Vinyl	
Backing:	100% Polyester Hi-Loft²™	
Weight:	650 gr/m ²	
Roll Width:	min. 137 cm	
Roll Length:	+/- 30 m	
Abrasion:	>300.000 cycles (MARTINDAL	E)
Cold Crack:	-23 °C	
UV-Resistance:	ISO 105 B02:≥ 7/8 (Blue Wool	Scale)
Flame retardancy*:	EU EN 1021 Part 1 & 2 EU IMO FTP 2010 Code MS (88) Part 8 3.1 & 3.2 EU ECE R 118.03 (R118.02 A EU EN 71-2:2006+A1:2007 Safety of Toys - Part 2: FI EU (MED) Marine Equipmen DE DIN 4102 (B2) IT UNI 9175 Classe 1.IM ES UNE 23.727-90 1R/M.2 FR NF P 92-503 (M2) AT ÖNORM B 3825 Gruppe AT ÖNORM A3800 Teil 1 US CAL TB 117-2013, Section	Anx. 6,7 & 8 lammabilit t Directive

*This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behaviour of this or any other material under actual fire conditions.

US FMVSS 302

US FAR 25/583

US NFPA 260 - Class 1

US ASTM E 84 Adhered - Class 1

FINISHES AND TREATMENTS PERMABLOK3®

Antibacterial Protection, Antimycotic Protection, Antifungal Protection, Anti-stain Finish, Mildew resistant backing and face, Sulfide Stain Resistant, Anti-static Finish, EN 71-3 Safety of Toys (Migration of certain elements)

ISO 18184:2019:1

Virucidal Activity: ISO 18184:2019: Coated Fabrics treated with PERMABLOK³⁰ are proven to reduce the presence of Coronavirus** by more than 90% within one hour of contact.

ISO 21702:2019:2

All the Coated fabrics treated with PERMABLOK^{3®} are capable of reducing the Coronavirus** activity by 99,9% within 24 hours of exposure on the surface.

Bacteriostatic Properties: ISO 22196:2011. Value of antibacterial*** activity R>2

SUSTAINABILITY eco/ense

ISO 14001 Enviromental Management REACH | RoHS, Carbon Neutral

SAMPLES AND ENQUIRES

samples: samples@vyvafabrics.nl | **orders**: info@vyvafabrics.nl

CARE AND CLEANING ₩ 🛛 🗡 🛇 🖂 🔀

For optimum care and cleaning please read the following instructions and recommendations.

Disinfectant Use

The following information refers to the performance of PERMABLOK3® products in specifics tests, conducted under laboratory conditions. Results may vary under actual conditions:

- Asepticare TB + II Antifect (in 0.5 % dilution) Caviwipes XL Packed
- Cleanisept Wipes Clorox Healthcare Bleach Germicidal Wipes
- Coverage Plus Germicidal Wipes Desomed rapid FD 366
- Hydrogen Peroxide Cleaner Disinfectant Wipes Instrunet Anionsurf
- Lysol Foaming Disinfectant Cleaner Microzid Oxivir TB Wipes
- Oxycide Diluted –3oz/gl in water PDI Sani-cloth bleach wipes
- Sanicloth AF 3 Sodium Hypochlorite. Disinfectant. Bletach cleaner. Dilution: 1:10 mix of bleach and water. • Surfanios Premium (in 0,25% dilution) • Surfa'Safe Premium (in 0,25% dilution) • Super Sani-cloth
- Virex II 256 (1:256 Dilution) Virox 5 Rtu Wet wipe Wex Cide 128 (1:128 dilution)

Rinse the area with clean water, then dry with a clean, lint-free cloth after using any disinfectants and cleaners.

Cleaning after Disinfection:

The coated fabric should be cleaned periodically in order to maintain its appearance and prevent build-up of dirt and contaminants. Any stain, spills, or soiling should be cleaned up immediately to prevent the possibility of permanent staining.

Use a mixture of 1:1 liquid soap (neutral pH) and water or our approved cleaning products for coated fabrics to remove stains on the surface of the material. Completely remove excess cleaner with a white, clean, damp cloth; and dry the surfaces afterwards. Lacquers, strong cleaners, detergents, xylene-based solutions, acetone, or ketone (MEK) cause immediate damage and contribute to the deterioration of the material. The use of such cleaners is at the owner's risk.

Cleaning methods to remove tougher stains

Step 1: Coffee, juice, red wine, sauces, chocolate, grease, crayon and suntan lotion. Remove excess spill with a damp cloth. Clean with a 1:1 mix of neutral liquid soap and water. Next, rinse with clean water and dry.

Step 2: Make-up Use a straight application of neutral PH soap. Wipe with a clean white cloth or soft brush, rinse with clean water, and dry.

Step 3: Blood, urine, faeces and all other tough stains Use a 1:10 mix of Isopropyl alcohol and water. Rinse thoroughly with clean water and dry.

For cleaning: use a soft white cotton cloth saturated with the recommended cleaning agent and rub the stain in random circles, ten times or more. Pat dry with another soft white cotton cloth and check the results. Do not use steel bristle brushes, abrasive scouring pads or metal, these cause permanent damage to the fabric. Methods 2 & 3 are not recommended for everyday cleaning! After cleaning, rinse the area with clean water, then dry with a clean, lint-free cloth. Failure to remove chemical residue will cause discolouration of the coated fabric surface to manifest itself earlier in the life cycle of the product.





















INFO@VYVAFABRICS.NL