







CHARACTERISTICS	S INDOOR - OUTDOOR
Composition:	92,5% Sunbrella Solution Dyed Acryl 7,5% Polyester
Weight:	596 gr/m²
Roll Width:	min. 137 cm
Roll Length:	+/- 32 m
Colour Fastness UV: Colour Fastness Rain:	7/8 ISO 105 B02 7/8 ISO 105 B04
Wet Crocking: Dry Crocking:	AATCC 8 with Grade 5 AATCC 8 with Grade 5
Pilling:	ASTM D3511 (Brush Pill), Class 3 minimum
Breaking Strength:	ASTM D5034 (Grab Test), 50 lbs / 22,5 kg Warp: 291 lbs / 132 kg Fill: 166 lbs / 75 kg
Seam Slippage:	ASTM D4034, 25 lbs / 11,25 kg Warp: 119 lbs / 54 kg Fill: 121 lbs / 55 kg
Flame retardancy*:	US CA 117-2013 Sec. E (CS-191-53) - Class 1 US UFAC Interior Fabrics Test Method-1990 - Class 1

\*This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behaviour of this or any other material under actual fire conditions.

### FINISHES AND TREATMENTS

Non-PFAS Water & Stain Repellent

# **SUSTAINABILITY**

OEKO-TEX® Standard 100

REACH

Greenguard

Lead Free

AZO Dye Free

# CARE AND CLEANING <u>™</u> △ ⊠ △ ⊗

For optimum care and cleaning please read the following instructions and recommendations.

#### Cleaning instructions

Brush off dirt before it becomes embedded in the fabric and wipe up spills or clean soon after a stain occurs. The quicker you clean spills and stains, the easier they can be to remove.

- Blot (don't rub) liquid spills with a clean, dry cloth.
   For oil-based spills, apply an absorbent such as corn starch, then remove with a straight edge.
- Spray on a mild cleaning solution of soap (such as Dawn or Woolite) and water.
- Rinse the fabric thoroughly to remove all soap residue.
- Air dry.

Tex'Aktiv Clean: Deep-acting, Powerful stain remover. Tex'Aktiv Guard: Stain protection, Beading effect.

## **SAMPLES AND ENQUIRES**

**samples**: samples@vyvafabrics.nl | **orders**: info@vyvafabrics.nl

















