

SLING LOGAN

Technical sheet



CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Composition	19 % Sunbrella Acrylic 22 % Polyester 59 % PVC		
Backing / Finish	Non PFAS		
Weave	Dobby		ISO 7211-1
Weight	480	g/m ²	ISO 3801
Width	137	cm	EN 1773
Roll length	40	ml	

FABRIC RESISTANCE

Tensile strength	210	220	daN/5cm	ISO 13934-1
Elongation at break	28	27	%	ISO 13934-1
Seam slippage (180 N)	<3	<3	mm	ISO 13936-2
Stitching strength	400	380	N	ISO 13935-2

COLOUR-FASTNESS

Colour fastness UV - outdoor - 1000h	4/5	Class / 5	ISO 105 B04
Colour fastness UV - indoor	8	Class / 8	ISO 105 B02
Colour fastness under dry friction	5	Class / 5	ISO 105X12
Colour fastness under wet friction	5	Class / 5	ISO 105X12
Colour fastness 30°C washing	5	Class / 5	ISO 105 C06

FIRE RESISTANCE

California Technical Bulletin 117-203 Section 1	Pass
NFPA 260 Classe I	Pass
NF EN 1021-1	Pass
BS 5852 Part 1 Source 0	Pass

USES

Guarantee	5	years
Recommended Uses	Seating, Cushions,	

CARE



This product's values may vary with a tolerance of ± 5%



VYVA
FABRICS
INDOOR & OUTDOOR
CONTRACT FURNITURE FABRICS

VYVA FABRICS
TT, VASUMWEG 140
1033 SH AMSTERDAM THE NETHERLANDS
TEL +31 (0)20 6599523 INFO@VYVAFABRICS.NL
WWW.VYVAFABRICS.NL