

GLOBE

INDOOR - OUTDOOR




2424  
SHETLAND



2399  
HEDGE



2454  
CONCRETE



2394  
PERSIAN GREEN



2458  
BROOK



2398  
IGUANA




2427  
ORCHARD



2429  
WOODBINE



2432  
APPLE



2433  
LAGOON



2380  
TUSK



2381  
PUTTY




2392  
HEMP



2383  
AUTUMN



2423  
PETROL



2431  
SHELL



2456  
PALE SMOKE



2384  
PECAN




2459  
TERRAIN



2382  
LANTERN



2430  
SASSY



2378  
SUGAR



2379  
QUICKSILVER



2455  
PATH



2389  
NUBIAN




2386  
SIZZLE



2385  
CLIFF



2393  
IRON



2421  
CARBON



2460  
OCTOPUS




2457  
PENNY




2388  
CASHEW



2390  
POOL




2434  
MAUVE




2397  
EBONY



2391  
BLUE BIRD




2395  
BAYOU



2426  
ADMIRAL



2425  
CELESTE



2396  
INDIGO



## CHARACTERISTICS

## INDOOR - OUTDOOR

Composition:	Topcoat: Vinyl
Backing:	100% Recycled Polyester
Weight:	695 gr/m <sup>2</sup>
Roll Width:	min. 137 cm
Roll Length:	+/- 27,4 m
Abrasion:	>300.000 cycles (MARTINDALE)
Cold Crack:	-32 °C
UV-Resistance:	ASTM G153-00a, Cycle 1, 1000 hours, UV co-efficient ≥7 (Blue Wool Scale)
Flame retardancy*:	EU EN 1021 Part 1 & 2 EU BS 5852 Source 0, 1 (Cigarette & Match) EU (MED) Marine Equipment Directive EU IMO MSC 88/26/ADD. 2 Part 8 3.1 & 3.2 (Replacing IMO A652) EU R118 DE DIN 4102 (B2) IT UNI ISO 3795 (FMVSS 302) FR NF P 92-503 (M2) US FAR 25/853 CH SN 198'898 & VKF AU AS.1530.3

\*This term and any corresponding data refer to the typical performance in the specific tests indicated and should not be construed to imply the behaviour of this or any other material under actual fire conditions.

## FINISHES AND TREATMENTS

PHthalate  
FREE

EN 71-3:2019 Migration of Certain Elements (Category III)  
99% reduction of bacteria on the surface of the coated fabric (ISO 22196)  
Bacteriostatic Properties: Mildew Resistant

## SUSTAINABILITY

Bromine-free, no Halogenated Flame Retardants (HFRs)  
No Bisphenol A (BPA)  
No Ozone Depleting Chemicals  
No PBTs (Persistent Bio accumulative and Toxic Chemicals)  
Contains bio-based renewable ingredients  
Phthalate free formulation  
Skin Safe (ISO 10993-10)  
REACH  
RoHS

## SAMPLES AND ENQUIRES

**samples:** [samples@vyvafabrics.nl](mailto:samples@vyvafabrics.nl) | **orders:** [info@vyvafabrics.nl](mailto:info@vyvafabrics.nl)

## CARE AND CLEANING



For optimum care and cleaning please read the following instructions and recommendations.

## Disinfectant Use

Here is a helpful list of products that you can use to disinfect:

**Clorox® Hydrogen Peroxide Disinfecting Cleaner,**

This kills bacteria and viruses in 30 seconds.

**BLEACH-RITE® Disinfecting Spray with Bleach,** Current Technologies  
This is a hospital-grade pre-mixed cleaner with bleach diluted 1:10.

**Dispatch® Hospital Cleaner Disinfectant Towels with Bleach**

This kills most bacteria and viruses in 1 minute.

**Bleach,** Dilute the bleach up to a 1:10 ratio (10%). Liberally apply diluted bleach solution using a sponge. Rinse with cold water several times. Wipe dry. Be sure to follow the guidelines on the bleach label.

**Isopropyl Alcohol** with concentration of around 70% can kill corona-viruses. Leave the 70% Isopropyl Alcohol solution on the product for one minute.

**Hydrogen Peroxide** with a 3% concentration can be used to disinfect. Apply to the product and allow to sit for one minute.

Rinse the area with clean water, then dry with a clean, lint-free cloth after using any disinfectants and cleaners.

## Cleaning after Disinfection:

The coated fabric should be cleaned periodically in order to maintain its appearance and prevent build-up of dirt and contaminants. Any stain, spills, or soiling should be cleaned up immediately to prevent the possibility of permanent staining.

Use a mixture of 1:1 liquid soap (neutral pH) and water or our approved cleaning products for coated fabrics to remove stains on the surface of the material. Completely remove excess cleaner with a white, clean, damp cloth; and dry the surfaces afterwards. Lacquers, strong cleaners, detergents, xylene-based solutions, acetone, or ketone (MEK) cause immediate damage and contribute to the deterioration of the material. The use of such cleaners is at the owner's risk.

## Cleaning methods to remove tougher stains

**Step 1:** Coffee, juice, red wine, sauces, chocolate, grease, crayon and suntan lotion. Remove excess spill with a damp cloth. Clean with a 1:1 mix of neutral liquid soap and water. Next, rinse with clean water and dry.

**Step 2:** Make-up. Use a straight application of neutral PH soap. Wipe with a clean white cloth or soft brush, rinse with clean water, and dry.

**Step 3:** Blood, urine, faeces and all other tough stains. Use a 1:10 mix of Isopropyl alcohol and water. Rinse thoroughly with clean water and dry.

For cleaning: use a soft white cotton cloth saturated with the recommended cleaning agent and rub the stain in random circles, ten times or more. Pat dry with another soft white cotton cloth and check the results. Do not use steel bristle brushes, abrasive scouring pads or metal, these cause permanent damage to the fabric. Methods 2 & 3 are not recommended for everyday cleaning! After cleaning, rinse the area with clean water, then dry with a clean, lint-free cloth. Failure to remove chemical residue will cause discolouration of the coated fabric surface to manifest itself earlier in the life cycle of the product.